



Contents lists available at ScienceDirect

Journal of Alloys and Compounds

journal homepage: www.elsevier.com/locate/jallcom

The effect of chromium (III) oxide (Cr_2O_3) nanopowder on the microstructure and cyclic hydrogen storage behavior of magnesium hydride (MgH_2)

Marek Polanski^a, Jerzy Bystrzycki^a, Robert A. Varin^{b,*}, Tomasz Plocinski^c, Marcin Pisarek^c^a Faculty of Advanced Technology and Chemistry, Military University of Technology, 2 Kaliskiego Str., 00-908 Warsaw, Poland^b Department of Mechanical and Mechatronics Engineering, University of Waterloo, 200 University Ave. W., Waterloo, Ontario, Canada N2L 3G1^c Faculty of Materials Science and Engineering, Warsaw University of Technology, 141 Woloska Str., 02-507 Warsaw, Poland

ARTICLE INFO

Article history:

Received 11 October 2010

Accepted 3 November 2010

Available online 10 November 2010

Keywords:

Solid state hydrogen storage

Ball milling

Magnesium hydride (MgH_2)Chromium oxide (Cr_2O_3)

Cycling

Microstructure

ABSTRACT

High energy ball milling in a Fritsch P6 planetary ball mill was used for the synthesis of the nanocomposite of MgH_2 with 10 wt.% of Cr_2O_3 nanopowder catalyst (particle size <50 nm). After ball milling for 1 h the resulting grain size of $\beta\text{-MgH}_2$ was equal to ~30 nm. Subsequently, the nanocomposite was subjected to 150 desorption/absorption cycles at 325 °C. A gradual loss of hydrogen storage capacity upon cycling from ~5.2 wt.% after 1 cycle to ~4.6 wt.% after 150 cycles is observed on respective PCT curves obtained at 325 °C after every 25 cycles. The TPD curves temperature maxima are gradually shifted to a higher temperature range with increasing number of cycles which may indicate a lowering of the overall rate of transformation. Thorough microstructural investigations using such techniques as X-ray diffraction (XRD), scanning transmission electron microscopy (STEM) and X-ray photoelectron spectroscopy (XPS) of the samples after 150 cycles of desorption/absorption show profound microstructural changes such as sintering of individual powder particles into agglomerates, increase in grain/crystallite size (>100 nm), segregation of the Cr_2O_3 particles to the interfaces between the sintered Mg particles and some reduction of Cr_2O_3 to Cr and MgO. All these microstructural changes seem to be responsible for the reduction of hydrogen storage capacity upon cycling and lowering the overall rate of transformation.

© 2010 Elsevier B.V. All rights reserved.